

CONSTRUCTION

EKOPUR LI

TWO COMPONENT POLYURETHANE SYSTEM

DESCRIPTION

Ekopur LI is two-component, non-foaming, rigid polyurethane system with good-electro insulation properties. Final material is obtained after mixing component A (mixture of polyols and additives) and component B (polymeric MDI based) in a given volume ratio. Application parameters of the system can be adjusted to customer specific requirements.

APPLICATION AND USE

Ekopur LI is used as a sealing material in electric cable joints.

ADVANTAGES

- Easy application
- Good mechanical properties
- Good electro-insulation properties



TECHNICAL DATA

The data below are laboratory data. They may vary in practice due to surface properties of the substrate, humidity, pressure, and other factors.

PROPERTIES

Parameter	Value
Density of component A at 25 °C	1.15 – 1.20 [g/cm ³]
Viscosity of component A at 25°C	3000 - 4000 mPas
Density of component B at 25 °C	1.22 – 1.24 [g/cm ³]
Viscosity of component B at 25°C	220 - 240 mPas
Mixing ratio A:B (by weight)	100 : 110
Mixing ratio A:B (by volume)	100 : 105
Gel time at 20 °C	30 – 60 [min]
Tack free time at 20 °C	40 – 100 [min]
Material density	1250 ± 50 [kg/m ³]
Shore hardness	65 ± 5 [°ShD]
Tensile strength	4 ± 1 [MPa]
Elongation at break	60 ± 2 [%]
Shrinkage	max 0.5 [%]
Surface resistance	>10 ¹² [Ω]
Volume resistance	>10 ¹² [Ω]
Reaction to fire	Self-extinguish

APPLICATION METHOD

Processing two-component polyurethane systems in order to obtain the final product may be carried out "by hand" or by using specialized equipment. In the manual method, it is necessary to mix carefully the components, avoiding aeration of the mixture. Machine method requires the two-component machine unit to mix the components in the continuous way.

SAFETY INSTRUCTIONS AND LIMITATIONS

When applying the product, use standard PPE meant for work with chemicals: safety gloves and goggles, protective clothing etc. Immediately change the clothes if they become soaked with components. For detailed safety information please see the Material Safety Data Sheet.

Failure to follow the application equipment operating manual and particularly its poor technical condition, insufficient cleaning and lack of maintenance, leads to a change in the ratio of supplied components which reduces material properties or makes the process completely impossible.

PACKAGING AND TRANSPORTATION

Adhesive components are packed into barrels/canisters with a capacity of 20 or 30 litres. Containers are delivered on pallets. After arranging with the customer, the material can be delivered in alternative packages (for instance 200 litres barrels or 1000 litres containers).

STORAGE AND SHELF LIFE

The component A and B shall be stored in airtight containers and in dry and well-ventilated areas at 10 - 30 °C.

The warranty period for properly stored components (A and B) is 6 months.

DISPOSAL

Follow local regulations.

APPROVALS AND CERTIFICATES

- Hygienic assessment (PZH)

DISCLAIMER

The Minova Logo is a registered trademark.

Copyright © 2019 Minova. All rights reserved

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

NS/TE/02/2016/045,046/ EkopurLI (November 2016)

ADDITIONAL DOCUMENTATION

- EKOPUR LI MSDS

LIST OF REPRESENTATIVES

- AUSTRIA: Minova MAI GmbH
- CZECH REPUBLIC: Minova Bohemia s.r.o.
- FRANCE / BELGIUM: Sales office Minova France / Belgium
- GERMANY: Minova CarboTech GmbH
- ITALY: Minova CarboTech GmbH Italy branch
- KAZAKHSTAN: Minova Kazakhstan LLP
- POLAND: Minova Ekochem S.A.; Minova Arnall Sp. z o.o.; Minova Ksante Sp. z o.o.
- RUSSIA: ZAO "Carbo-ZAKK"
- SLOVAKIA: Minova Bohemia s. r. o., organizačná zložka
- SOUTH AFRICA: Minova Africa (Pty) Ltd.
- SPAIN: Minova Codiv S.L.U.
- SWEDEN / NORWAY: Minova Nordic AB
- UNITED KINGDOM: Minova Weldgrip Ltd.; Minova International Ltd.
- APAC: Minova Australia Pty Ltd.
- AMERICAS: Minova USA Inc.

CUSTOMER SERVICE

For additional support options available at your area, contact our local offices.

www.minovaglobal.com