

CONSTRUCTION

Minotop 60

HIGHLY FLUID BACKFILLING GROUT

DESCRIPTION

Minotop 60 is a single component mineral and cement-based dry pre-bagged grout. After blending with the appropriate amount of water creates a highly fluid. It is designed especially for backfilling on long distance between injection points.

APPLICATION AND USE

- Filling voids (cavities) between GRP tube and the substrate
- Filling backfill voids

ADVANTAGES

- Self-compacting nature eliminates honeycombing and displaces air without vibration
- No bleeding
- Ease and safety of use
- Pre-bagged to overcome site-batched variations – only the site addition of clean water is required
- High strength gain
- Non-flammable



TECHNICAL DATA

The data below are laboratory data. They may vary in practice due to surface properties of the substrate, humidity, pressure, and other factors.

PRODUCT CHARACTERISTICS

Reference	Minotop 60
Compressive strength (EN 196-1)	≥ 60 MPa
Consistence (EN 12350-5)	F6 / fluid
Density of fresh grout	1850 ± 50 kg/m ³
Flammability	non-flammable (A1)

COMPONENT CHARACTERISTICS

Reference	Minotop 60
Colour / form	grey powder
Consumption	1.44 – 1.52 kg/ltr
Water per 25 kg bag	6.0 – 6.5 ltr
Pot life ¹	60 min

1. 20 °C; 28 days

APPLICATION METHOD

1. Surface Preparation

Before application of Minotop 60 remove loose fragments of rock, concrete, dust, greasy stains, formwork release agent etc. In order to improve adhesion to the substrate surface it is recommended to dump it with water prior to application. For the best results, wet the concrete surface 24 hours before performing the application if necessary.

2. Equipment

Small quantities can be mixed in a suitably sized drum using a spiral paddle with a slow speed (400/500 rpm) heavy-duty drill.

Greater quantities should be mixed using a forced-action mixer.

3. Execution

If mixing small quantities by hand, add one bag 25 kg of the Minotop 60 powder to 6,0 – 6,5 litres of drinking quality water. This should be mixed vigorously for a minimum of 3 minutes.

For larger volumes, measure 5,0 litres of drinking quality water and pour $\frac{3}{4}$ into the mixer (per one 25 kg bag) and, with the machine in operation, add one full 25 kg bag of Minotop 60 and mix for one minute before adding the rest of the water. Then mix for a minimum of 3 minutes. Do not subsequently re-temper with extra water.

Note: in all cases Minotop 60 powder must be added to water.

In case of use continuous mixing placers (e.g. MAI 4YOU, PFT G-4) follow equipment manufacturer’s guidelines.

Free-fall mixers are not recommended.

4. Cleaning

Clean tools with water. When hardened clean mechanically.

5. Curing

Minotop 60 does not requires curing when used in confined spaces, however under strong drying conditions Minotop 60 should be cured immediately after finishing in accordance with good concrete practice. In very fast drying conditions, supplementary curing with polythene sheeting taped down at the edges should be used.

In cold conditions, the material must be protected from freezing.

SAFETY INSTRUCTIONS AND LIMITATIONS

It is recommended that gloves, eye protection and a dust mask are used when using Minotop 60. For more details refer to our Material Safety Data Sheet.

The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

PACKAGING AND TRANSPORTATION

25 kg valve sack, 40 bags per pallet. Other packing on request.

STORAGE AND SHELF LIFE

Shelf life 6 months when stored in dry and cool conditions (between 5 and 40°C).

DISPOSAL

Follow local regulations.

APPROVALS AND CERTIFICATES

- Hygienic Certificate HK/B/0533/02/2015

DISCLAIMER

The Minova Logo is a registered trademark.

Copyright © 2019 Minova. All rights reserved

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

ME-NS/TE/03/156-02/ Minotop 60 e02 (April 2015)

ADDITIONAL DOCUMENTATION

- Minotop 60 MSDS

LIST OF REPRESENTATIVES

- AUSTRIA: Minova MAI GmbH
- CZECH REPUBLIC: Minova Bohemia s.r.o.
- FRANCE / BELGIUM: Sales office Minova France / Belgium
- GERMANY: Minova CarboTech GmbH
- ITALY: Minova CarboTech GmbH Italy branch
- KAZAKHSTAN: Minova Kazakhstan LLP
- POLAND: Minova Ekochem S.A.; Minova Arnall Sp. z o.o.; Minova Ksante Sp. z o.o.
- RUSSIA: ZAO "Carbo-ZAKK"
- SLOVAKIA: Minova Bohemia s. r. o., organizačná zložka
- SOUTH AFRICA: Minova Africa (Pty) Ltd.
- SPAIN: Minova Codiv S.L.U.
- SWEDEN / NORWAY: Minova Nordic AB
- UNITED KINGDOM: Minova Weldgrip Ltd.; Minova International Ltd.
- APAC: Minova Australia Pty Ltd.
- AMERICAS: Minova USA Inc.

CUSTOMER SERVICE

For additional support options available at your area, contact our local offices.

www.minovaglobal.com