

CONSTRUCTION

CARBO PUR20

HIGH-GRADE DUAL-COMPONENT POLYURETHANE ADHESIVE



DESCRIPTION

CARBO PUR 20 is a high-grade dual-component polyurethane adhesive, water- and solvent-free.

Component A is a polyol filled with mineral substances and added processing aids.
Component B is a polyisocyanate on MDI-basis.

After mixing the components, a creamy and easily spreadable adhesive is obtained.



APPLICATION AND USE

CARBO PUR20 is recommended for mosaic-, vertical lamella-, lam-, strip- and multi-layer parquet and also for solid planks and wood-block RE and WE.

Suitable for surfaces with integrated floor heating.

ADVANTAGES

- Facilitates rapid, secure working
- Suitable for swell-resistant of woods that make high demands on adhesive techniques
- To be used on absorbent and non-absorbent layers
- Low emission values

TECHNICAL DATA

The specified data refer to standard conditions (23 °C / 50 % rel. hum.). Deviating room air conditions change the times.

MATERIAL DATA

Parameter	Component A	Component B	Standard
Density at 25° C	1700 ± 50 kg/m ³	1234 ± 50 kg/m ³	DIN 12791-1
Colour	light ivory	dark brown	-
Mixed colour	beige		-

REACTION DATA

Parameter	Details	Unit
Mixing ratio A : B (parts per weight)	7.5 : 1.0	-
Pot life (23 °C)	45	minutes
Laying period (23 °C)	60 - 90	minutes
Load bearing after	48	hours

MECHANICAL DATA

Parameter	Value	Unit	Standard
Shore D hardness	65 - 72	-	ISO 7619-1
Tensile shearing strength after 3 d	5 - 7	MPa	DIN EN 14293
Tensile strength 7 d (30 °C / 80 % r. h.)	5 - 6	MPa	ISO 527-2
Elongation at break	16 - 19	%	ISO 527-2

APPLICATION METHOD

1. Requirements for the subfloor

The subfloor as well as the room climate need to be subject to DIN 18356. Subfloors must be absorbent, permanently dry, dust free, even, free of cracks, impurities and substances inhibiting adhesion.

Screed with integrated floor heating systems must be prepared with primer CARBO P-Grund10. Consider drying time of primer.

2. Laying

Empty the hardener container completely into the resin container. Stir the mixture in the container for at least 3 minutes, using a portable drill equipped with a mixing disk. Take care on good mixture; especially at the container edge and bottom. Apply adhesive to the surface using a notched trowel. Position the parquet and tap down. Ensure that there is a good adhesive contact to the parquet underside. Leave a gap of 1 – 2 cm between wall and parquet flooring. After a drying period between 24 - 48 hours, the parquet may be polished and sealed.

Apply only at a processing temperature of 15 °C – 30 °C and within an air humidity below 65 %.

3. Adhesive consumption

Application						
Mosaic parquet according to DIN-EN 13488	Vertical lamella parquet according to DIN-EN 14761	Lam parquet up to 10 mm according to DIN-EN 13227	Strip parquet according to DIN-EN 13226	Solid planks according to DIN-EN 13629	Multi-layer parquet according to DIN-EN 13489	Wood-block RE and WE according to DIN 68 702
Trowel notch size						
TKB B3	TKB B5 TKB B10	TKB B5	TKB B5 TKB B11	TKB B12 TKB B15	TKB B5 TKB B12	TKB B12 TKB B15
Consumption 700g - 1500 g/m ² depending on subsurface and parquet						

4. Final product

After 24 - 48 hours, the parquet adhesive is hardened to a tough, permanent elastic and hydrolysis-resistant adhesive, which absorbs and reduces tensions in the bond. Hardening will be delayed through low temperatures (< 15 °C), however a stop of the reaction is not to be expected. The adhesive hardens completely.

SAFETY INSTRUCTIONS AND LIMITATIONS

Observe the usual precautionary measures for handling chemicals, see MSDS.

If it is necessary to apply the adhesive in cold weather, the adhesive must be permitted to warm up to the adequate working temperature. Observe the instructions for installation provided by the flooring manufacturer as well as all other available norms and data sheets.

Avoid freezing.

PACKAGING AND TRANSPORTATION

All forms of packing are approved to the danger goods regulation road, railway, domestic shipping. The components can be delivered in 0.75/1/6.2/11.5 l units. Other packaging units are available on request. Details are shown in the offer.

STORAGE AND SHELF LIFE

At least six months after delivery when stored in a dry place between 10 °C und 30 °C. When this time is exceeded, we recommend having the material checked by Minova for compliance with specification. Observe legal storage specifications (see safety data sheet).

DISPOSAL

Follow local regulations.

APPROVALS AND CERTIFICATES

1. General approval of construction regulation Z-155.10-37 (**DIBt**, Berlin 2010)

DISCLAIMER

The Minova Logo is a registered trademark.

Copyright © 2019 Minova. All rights reserved

The data in this sheet conform to our best knowledge and experience at the date of printing, which is indicated below. The state of knowledge and experience are evolving constantly. Please pay attention therefore, that you always refer to the current version of this data sheet.

The description of the product application in this sheet cannot take the special conditions and circumstances into account emerging from the individual case. Please check our product therefore in any case prior to use for its suitability in the actual application. Application, use and processing of our product is outside of our control capabilities. That is why they as well as the processing result achieved based on our information are exclusively subject to your own responsibility.

No data in this sheet constitute a guarantee in a legal sense. It is clarified that our liability is limited

to the contractual acknowledgements for the purchase of this product. This is a translation. Minova assumes no responsibility for the correctness of the translation. Only the original German version of the data sheet is binding.

402812/001001/CARBO PUR20_E27 of February 2019

ADDITIONAL DOCUMENTATION

- MSDS of CARBO PUR20 component A
- MSDS of CARBO PUR20 component B

LIST OF REPRESENTATIVES

- AUSTRIA: Minova MAI GmbH
- CZECH REPUBLIC: Minova Bohemia s.r.o.
- FRANCE / BELGIUM: Sales office Minova France / Belgium
- GERMANY: Minova CarboTech GmbH
- ITALY: Minova CarboTech GmbH Italy branch
- KAZAKHSTAN: Minova Kazakhstan LLP
- POLAND: Minova Ekochem S.A.; Minova Arnall Sp. z o.o.; Minova Ksante Sp. z o.o.
- RUSSIA: ZAO "Carbo-ZAKK"
- SLOVAKIA: Minova Bohemia s. r. o., organizačná zložka
- SOUTH AFRICA: Minova Africa (Pty) Ltd.
- SPAIN: Minova Codiv S.L.U.
- SWEDEN / NORWAY: Minova Nordic AB
- UNITED KINGDOM: Minova Weldgrip Ltd.; Minova International Ltd.
- APAC: Minova Australia Pty Ltd.
- AMERICAS: Minova USA Inc.

CUSTOMER SERVICE

For additional support options available at your area, contact our local offices.

www.minovaglobal.com